

No.: GZIN1706026655MR

Date: Jun 21, 2017

Page: 1 of 5

CUSTOMER NAME:

SHENZHEN FULLGO SECURITY PACKAGING TECHNOLOGY CO., LTD

ADDRESS:

ROOM 312, NO.9 BUILDING. LONGYIN ROAD, XIXIANG, BAOAN DISTRICT,

SHENZHEN, P. R. CHINA

Sample Name

: SECURITY VOID FILM MATERIAL-TOTAL TRANSFER

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No.

: CP17-031913-SZ-2.2

Date of Receipt

: Jun 13, 2017

Testing Start Date

: Jun 13, 2017

Testing End Date

: Jun 21, 2017

Test result(s)

: For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for

SGS-CSTC Standards Technical Services Co., Ltd. GZ Branch Testing

Center

Kelly Lee

Authorized signatory





No.: GZIN1706026655MR

Date: Jun 21, 2017

Page: 2 of 5

Summary of Results:


| No. | Test Item | Test Method | Result | Conclusion |
|-----|--|---------------------------------------|-----------------------------|------------|
| 1 | 180° Peel Strength ISO 29862:2007 Method 1 | | Maximum Strength: 3.5N/10mm | / |
| 2 | 180º Peel Strength | JIS Z0237:2009 Section 10 Method 1 | Maximum Strength: 3.6N/10mm | / |

Note: Pass : Meet the requirements;

Fail: Does not meet the requirements;

/: Not Apply to the judgment.

Original Sample Photo:







No. : GZIN1706026655MR

Date: Jun 21, 2017

Page: 3 of 5

1. Test Item: 180º Peel Strength Sample Description: See photo

Test Method: ISO 29862:2007 Method 1

Test Condition:

Specimen width: 24mm
Testing speed: 300mm/min

Lab Environmental Condition: (23±2)°C, (50±5)%RH


Test Result:

| Test Item | Test Result | |
|-------------------------------------|-----------------------------|--|
| 190º Deal Strangth (to steel panel) | Maximum Strength: 3.5N/10mm | |
| 180º Peel Strength (to steel panel) | (See note 1) | |

Note:

- 1. The result was for reference only as the adhesive breaks during the test.
- 2. Test specimens were cut from the sample.

Test Photo:





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.sexx and, for leactonic format document subject to Terms and Conditions for Electronic Document at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-en/Condit



No.: GZIN1706026655MR

Date: Jun 21, 2017

Page: 4 of 5

Equipment Information:

| Equipment | Model | Equipment No. | Calibration date | Next Calibration date |
|----------------------------|-------|---------------|------------------|-----------------------|
| Universal Testing Machine | Z010 | GZMR-PL-E109 | 2016-10-12 | 2017-10-11 |

Test Item: 180º Peel Strength
 Sample Description: See photo

Test Method: JIS Z0237:2009 Section 10 Method 1

Test Condition:

Specimen width: 24mm
Testing speed: 300mm/min

Lab Environmental Condition: (23±2)°C, (50±5)%RH

Test Result:

| Test Item | Test Result | |
|-------------------------------------|-----------------------------|--|
| 180º Peel Strength (to steel panel) | Maximum Strength: 3.6N/10mm | |
| 160- Feel Strength (to steel paner) | (See note 1) | |

Note:

- 1. The result was for reference only as the adhesive breaks during the test.
- 2. Test specimens were cut from the sample.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.ags.com/en/Terma-and-Conditions.aepx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.ags.com/en/Terms-and-ConditionsTerms-e-Document.aepx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of the service of the contained that the service of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the eample(s) tested and such sample(s) are retained for 30 days only.





No.: GZIN1706026655MR

Date: Jun 21, 2017

Page: 5 of 5

Test Photo:





Equipment Information:

| Equipment | Model | Equipment No. | Calibration date | Next Calibration date |
|------------------------------|-------|---------------|------------------|-----------------------|
| Universal Testing Machine | Z010 | GZMR-PL-E109 | 2016-10-12 | 2017-10-11 |

******* End of report*******



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.sexx and, for leactonic format document subject to Terms and Conditions for Electronic Document at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-en/Condit